NC/QC/YPD/SIP-05/2017-18/SP-C1 Date: 09-03-2018

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

PHYSICAL TESTS ON CEMENT

Brand : ULTRA TECH
Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**158 min**	Shall not be less than 30 min
2	Final setting time	**272 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.19 %**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**2.11 mm**	Shall not be more than 10 mm
5	Compressive strength a) 3 days (average of three results)	**28.45 N/Sq mm**	Shall not be less than 27 N/Sqmm

KIRAN. R
M.E, (Civil-

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Newzen Consultants Bangalore

NC/QC/YPD/SIP-05/2017-18/SP-PCC1 Date: 09-03-2018

1. TESTING OF COARSE AND FINE AGGREGATES:

Sub: Testing of Coarse and Fine aggregates to be used for bed concrete.
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

1. COARSE AGGRGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2007) % Passing	
	40 mm Sample	Single size	Graded
40mm	**100.00**	85-100	90 – 100
20mm	**68.25**	0 -20	30- 70
10mm	**18.45**	0 -5	10- 35
4.75mm	**4.30**	------	0- 5

2. FINE AGGREGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	**98.45**	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	**87.15**	60-95	75-100	85-100	
01.18	**72.05**	30-70	55-90	75-100	
600.mic	**48.65**	15-34	35-59	60-79	
300.mic	**18.70**	5-20	8-30	12-40	
150.mic	**8.15**	0-10	0-10	0-10	

K...R
KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YPD/SIP-05/2017-18/SP-C2 Date: 13-03-2018

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

PHYSICAL TESTS ON CEMENT

Brand : ULTRA TECH
Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**153 min**	Shall not be less than 30 min
2	Final setting time	**268 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.18 %**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**2.09 mm**	Shall not be more than 10 mm
5	Compressive strength b) 3 days (average of three results)	**28.78 N/Sq mm**	Shall not be less than 27 N/Sqmm

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/YPD/SIP-05/2017-18/SP-PCC2 Date: 13-03-2018

1. TESTING OF COARSE AND FINE AGGREGATES:

Sub: Testing of Coarse and Fine aggregates to be used for bed concrete.
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

1. COARSE AGGRGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2007) % Passing	
	40 mm Sample	Single size	Graded
40mm	100.00	85-100	90 – 100
20mm	67.45	0 -20	30- 70
10mm	19.30	0 -5	10- 35
4.75mm	3.95	------	0- 5

2. FINE AGGREGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	96.20	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	84.35	60-95	75-100	85-100	
01.18	71.10	30-70	55-90	75-100	
600.mic	47.60	15-34	35-59	60-79	
300.mic	19.85	5-20	8-30	12-40	
150.mic	8.10	0-10	0-10	0-10	

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Newzen Consultants Bangalore

NC/QC/YPD/SIP-05/2017-18/SP-SSM1

Date: 13-03-2018

1. TESTING OF STONE SAMPLE :

Sub: Testing of Size stone.
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.
Technical Reference: IS 1121(Part 1) -1974 (R.A on 1998)

AE

Table 1.1 :

SL No	Details of Tests	Observed Value	Normal Values
01	Compressive Strength	**1375.00** Kg/ Sqcm	Not less than 1000.00 Kg/Sqcm
02	Water absorption,%	**0.37 %**	Not more than 2.0 %

KIRAN. P
M.E, (Civil-E

AE

For Newzen Consultants Bangalore

Proprietor

NC/QC/YPD/SIP-05/2017-18/SP-C3

Date: 15-03-2018

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

PHYSICAL TESTS ON CEMENT

Brand : ULTRA TECH
Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**159 min**	Shall not be less than 30 min
2	Final setting time	**271 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**1.94 %**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**2.18 mm**	Shall not be more than 10 mm
5	Compressive strength a) 3 days (average of three results)	**28.79 N/Sq mm**	Shall not be less than 27 N/Sqmm

K.R

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Newzen Consultants Bangalore

NC/QC/YPD/SIP-05/2017-18/SP-FA1 **Date: 15-03-2018**

1. TESTING OF FINE AGGREGATES :

Sub: Testing of Fine Aggregates.
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

TABLE - 1.1 : SIEVE ANALYSIS :

IS Sieve Size,mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -II	
04.75	**95.45**	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	**88.15**	60-95	75-100	85-100	
01.18	**72.00**	30-70	55-90	75-100	
600. mic	**54.85**	15.34	35-59	60-79	
300.mic	**22.45**	5-20	8-30	12-40	
150.mic	**7.35**	0-10	0-10	0-10	

TABLE 1.2 ;

Sl No	Test Conducted	Sample	Results	**Requirements** as Per IS. Specification IS :383-1970 (Reaffirmed 2002)
1	Bulking of Sand	001	**15.12 %**	-----
2	Silt Content	----	**0.52 %**	Not more than 8%
3	Specific Gravity	----	**2.61**	-------

KIRAN. R
M.E, (Civil-Engg)

Page No. 1/1,

AE

For Newzen Consultants Bangalore

Proprietor

NC/QC/YPD/SIP-05/2017-18/SP-CA1

Date: 15-03-2018

1. TESTING OF COARSE AGGREGATES (20 mm):

Sub: Testing of Construction Materials.
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

Table - 1.1 : SIEVE ANALYSIS :

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2002) % Passing	
	20 mm Sample	Single size	Graded
40 mm	100.00	100.00	100.00
20 mm	97.25	85-100	90 - 100
10 mm	39.15	0 - 20	25 - 55
4.75 mm	4.10	0 - 5	0 - 10

TABLE 1.2 :

SL No	Test conducted	Results	Requirements as per IS:383-1970 & Tests Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2002)
1.	Flakiness Index	23.15 %	Not to exceed 25 %
2.	Crushing value	26.42 %	Not to exceed 45 % for concrete other than for wearing surfaces and 30% for concrete for wearing surfaces

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YPD/SIP-05/2017-18/SP-S1

Date: 15-03-2018

1. TEST REPORT ON REINFORCEMENT STEEL:

Sub: Testing of Reinforcement Steel of diameter 10 & 12 mm **TMT Steel.**
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

TABLE – 1

SL No	Details	For 10 mm		For 12 mm	
		Test Results	Min Req. as per IS 1786-2008	Test Results	Min Req. as per IS 1786-2008
01	Observed diameter of bar	**10.0 mm**	10.0 mm	**12.0 mm**	12.0 mm
02	Observed Wt/m Length **Kg/m**	**0.621**	0.567	**0.882**	0.834
03	Proof stress/Yield stress, fy , **N/mm^2**	**558.0**	500.0	**554.0**	500.0
04	Bend/ Re bend Test	**Ok**	---	**Ok**	---
05	Percentage of Elongation, %	**20.60**	12.00	**21.20**	12.00
06	Ultimate Tensile Strength **N/mm^2**	**642.0**	545.0	**637.0**	545.0

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YPD/SIP-05/2017-18/SP-CB1

Date: 23-03-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	16-03-18	23-03-18	07	22500	395	17.56	**17.19**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	380	16.89	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YPD/SIP-05/2017-18/SP-CB2

Date: 24-03-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements Road and Drain at Srinivasapura in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	17-03-18	24-03-18	07	22500	400	17.78	**17.78**
	002	"	"	"	"	395	17.56	
	003	"	"	"	"	405	18.00	

K...R
KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com